


3ml Glass Syringe – Control with metal luer lock



Tomopal Part # 140-3503

Piston Outside Diameter:	9.35 mm ± 0.10 mm
D) Barrel Diameter Outside:	11.75 mm ± 0.25 mm
L) Length:	142.50 mm ± 0.50 mm
Increment:	0.2 ml
Volume:	3.0 ml ±1.5% of volume

- The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at luer lock tip and barrel base, the points at which most breakage occur.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes are available in universal fit or custom fit design. The custom fit syringes are uniquely numbered for matching.
- The metal luer lock tip meets the specification of American National Standards for Medical Materials luer taper fitting performance, HIMA MD 70.1 - 1983.
- The fitting is made from chrome-plated brass and fits all female luer lock fittings.
- The syringe is clearly marked with graduations of 1 and 5 ml. The graduations are permanently fused for lifetime legibility.

Glass Properties:

<table border="0"> <tr> <td>Expansion coefficient:</td> <td>52 +/- 10⁻⁷ / Centigrade</td> </tr> <tr> <td>Density:</td> <td>2.36g +/- 0.03g CM³</td> </tr> <tr> <td>Modulus of elasticity:</td> <td>64 +/- 10³ mm⁻²</td> </tr> <tr> <td>Water resistance:</td> <td>First Class</td> </tr> <tr> <td>Acid resistance:</td> <td>First Class</td> </tr> <tr> <td>Alkali resistance:</td> <td>First Class</td> </tr> </table>	Expansion coefficient:	52 +/- 10 ⁻⁷ / Centigrade	Density:	2.36g +/- 0.03g CM ³	Modulus of elasticity:	64 +/- 10 ³ mm ⁻²	Water resistance:	First Class	Acid resistance:	First Class	Alkali resistance:	First Class	<table border="0"> <tr> <td>Softening point:</td> <td>785 @ degrees centigrade</td> </tr> <tr> <td>Melting temperature:</td> <td>1260 @ degrees centigrade</td> </tr> <tr> <td>Strain point:</td> <td>525 @ degrees centigrade</td> </tr> <tr> <td>Annealing point:</td> <td>570 @ degrees centigrade</td> </tr> <tr> <td>Hardness:</td> <td>7</td> </tr> <tr> <td>Color:</td> <td>Clear</td> </tr> </table>	Softening point:	785 @ degrees centigrade	Melting temperature:	1260 @ degrees centigrade	Strain point:	525 @ degrees centigrade	Annealing point:	570 @ degrees centigrade	Hardness:	7	Color:	Clear
Expansion coefficient:	52 +/- 10 ⁻⁷ / Centigrade																								
Density:	2.36g +/- 0.03g CM ³																								
Modulus of elasticity:	64 +/- 10 ³ mm ⁻²																								
Water resistance:	First Class																								
Acid resistance:	First Class																								
Alkali resistance:	First Class																								
Softening point:	785 @ degrees centigrade																								
Melting temperature:	1260 @ degrees centigrade																								
Strain point:	525 @ degrees centigrade																								
Annealing point:	570 @ degrees centigrade																								
Hardness:	7																								
Color:	Clear																								