


## 20ml Glass Syringe – Control



Tomopal Part #	140-3520
Piston Outside Diameter:	$20.35 \text{ mm} \pm 0.25 \text{ mm}$
D) Barrel Diameter Outside:	24.20 mm ± 0.35 mm
L) Length:	182.00 mm $\pm$ 0.50 mm
Increment:	1.0 ml
Volume:	20.0 ml 1.5% of volume

- The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at luer lock tip and barrel base, the points at which most breakage occur.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes are available in universal fit or custom fit design. The custom fit syringes are uniquely numbered for matching.
- The metal luer lock tip meets the specification of American National Standards for Medical Materials luer taper fitting performance, HIMA MD 70.1 1983.
- The fitting is made from chrome-plated brass and fits all female luer lock fittings.
- The syringe is clearly marked with graduations of 2.0 ml. The graduations are permanently fused for lifetime legibility.

## **Glass Properties:**

Centigrade Softening point	nt: 785 @ degrees centigrade
3g CM <sup>3</sup> Melting tempe	erature: 1260 @ degrees centigrade
m <sup>-2</sup> Strain point:	525 @ degrees centigrade
Annealing poi	nt: 570 @ degrees centigrade
Hardness:	7
Color:	Clear
	3g CM <sup>3</sup> Melting tempo   nm <sup>-2</sup> Strain point:   Annealing poi   Hardness: