
## **100ml Glass Syringe**

with 3/8" UNF Threaded Nut



Tomopal Part #	140-4604
Piston Outside Diameter:	$35.90 \text{ mm} \pm 0.25 \text{ mm}$
D1) Barrel Diameter Outside:	$41.20 \text{ mm} \pm 0.75 \text{ mm}$
D2) Barrel Collar Diameter:	55.50 mm $\pm$ 0.75 mm
D3) Piston Collar Diameter:	$42.05 \text{ mm} \pm 0.65 \text{ mm}$
L) Length:	$215.00 \text{ mm} \pm 0.65 \text{ mm}$
Increment:	5.0 ml
Volume:	100.0 ml ±1.5% of volume

## **Features:**

- The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at 3/8" UNF threaded tip and barrel base, the points at which most breakage occur.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes available in universal fit or custom fit design. The custom fit syringes are uniquely numbered for matching.
- The fitting is made from chrome-plated brass or SS-316.
- The syringe is clearly marked with graduations of 5.0 ml and 10.0 ml. The graduations are permanently fused for lifetime legibility.

## **Glass Properties:**

Expansion coefficient:	52 +/- 10 <sup>-7</sup> / Centigrade	Softening point:	785 @ degrees centigrade
Density:	2.36g +/- 0.03g CM <sup>3</sup>	Melting temperature:	1260 @ degrees centigrade
Modulus of elasticity:	64 +/- 10 <sup>3</sup> mm <sup>-2</sup>	Strain point:	525 @ degrees centigrade
Water resistance:	First Class	Annealing point:	570 @ degrees centigrade
Acid resistance:	First Class	Hardness:	7
Alkali resistance:	First Class	Color:	Clear

Tel: 916.429.7240 Fax: 916.429.2701