
## **10ml Glass Syringe**

with 1/4" UNF Threaded Nut



Tomopal Part #	140-7010
Piston Outside Diameter:	15.15 mm ± 0.15 mm
D1) Barrel Diameter Outside:	18.35 mm $\pm$ 0.35 mm
D2) Barrel Collar Diameter:	$26.20 \text{ mm} \pm 0.75 \text{ mm}$
D3) Piston Collar Diameter:	19.95 mm $\pm$ 0.60 mm
L) Length:	129.50 mm $\pm$ 0.50 mm
Increment:	0.2 ml
Volume:	10.0 ml ±1.5% of volume

## **Features:**

- The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at 1/4" UNF threaded tip and barrel base, the points at which most breakage occurs.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes are available in custom fit design. The custom fit syringes are uniquely numbered for matching piston and barrel.
- The 1/4" UNF threaded nut fitting is made from stainless steel.
- The syringe is clearly marked with graduations of 0.2 ml and 1.0 ml. The graduations are permanently fused for lifetime legibility.

## **Glass Properties:**

Expansion coefficient:	52 +/- 10 <sup>-7</sup> / Centigrade	Softening point:	785 @ degrees centigrade
Density:	2.36g +/- 0.03g CM <sup>3</sup>	Melting temperature:	1260 @ degrees centigrade
Modulus of elasticity:	64 +/- 10 <sup>3</sup> mm <sup>-2</sup>	Strain point:	525 @ degrees centigrade
Water resistance:	First Class	Annealing point:	570 @ degrees centigrade
Acid resistance:	First Class	Hardness:	7
Alkali resistance:	First Class	Color:	Clear