


100ml Glass Syringe

with 1/4" UNF Threaded Nut



Tomopal Part # 140-7100

Piston Outside Diameter: $35.90 \text{ mm} \pm 0.25 \text{ mm}$ D1) Barrel Diameter Outside: $41.20 \text{ mm} \pm 0.75 \text{ mm}$ D2) Barrel Collar Diameter: $55.50 \text{ mm} \pm 0.75 \text{ mm}$ D3) Piston Collar Diameter: $42.05 \text{ mm} \pm 0.65 \text{ mm}$ L) Length: $216.00 \text{ mm} \pm 0.65 \text{ mm}$

Increment: 5.0 ml

Volume: 100.0 ml $\pm 1.5\%$ of volume

Features:

- · The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at 1/4" UNF threaded tip and barrel base, the points at which most breakage occur.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- · The syringes are available in custom fit design. The custom fit syringes are uniquely numbered for matching piston and barrel.
- The 1/4" UNF threaded nut fitting is made from stainless steel.
- · The syringe is clearly marked with graduations of 5.0 ml and 10.0 ml. The graduations are permanently fused for lifetime legibility.

Glass Properties:

Expansion coefficient:	52 +/- 10 ⁻⁷ / Centigrade	Softening point:	785 @ degrees centigrade
Density:	2.36g +/- 0.03g CM ³	Melting temperature:	1260 @ degrees centigrade
Modulus of elasticity:	64 +/- 10 ³ mm ⁻²	Strain point:	525 @ degrees centigrade
Water resistance:	First Class	Annealing point:	570 @ degrees centigrade
Acid resistance:	First Class	Hardness:	7
Alkali resistance:	First Class	Color:	Clear