


5ml Glass Syringe

with metal luer lock



Tomopal Part # 140-4005

Piston Outside Diameter:12.60 mm ± 0.10 mmD1) Barrel Diameter Outside:15.40 mm ± 0.30 mmD2) Barrel Collar Diameter:22.25 mm ± 0.75 mmD3) Piston Collar Diameter:17.25 mm ± 0.55 mmL) Length:105.00 mm ± 0.50 mm

Increment: 0.2 ml

Volume: 5.0 ml $\pm 1.5\%$ of volume

Features:

- The syringe is made from heat resistant borosilicate glass.
- · The material and construction is resistant to breakage from shock and sudden temperature changes.
- It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at luer lock tip and barrel base, the points at which most breakage occur.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes are available in custom fit design. The custom fit syringes are uniquely numbered for matching piston and barrel.
- The metal luer lock tip meets the specification of American National Standards for Medical Materials luer taper fitting performance,
 HIMA MD 70.1 1983
- The metal luer lock fitting is made from chrome-plated brass and fits all female luer lock fittings.
- · The syringe is clearly marked with graduations of 0.2 and 1.0 ml. The graduations are permanently fused for lifetime legibility.

Glass Properties:

Expansion coefficient: $52 + /- 10^{-7}$ / CentigradeDensity:2.36g + /- 0.03g CM3Modulus of elasticity: $64 + /- 10^3$ mm $^{-2}$ Water resistance:First ClassAcid resistance:First ClassAlkali resistance:First Class

Softening point:785 @ degrees centigradeMelting temperature:1260 @ degrees centigradeStrain point:525 @ degrees centigradeAnnealing point:570 @ degrees centigradeHardness:7

Tel: 916.429.7240

Fax: 916.429.2701

Color: Clear