

150ml Glass Syringe

with metal luer lock



Tomopal Part # 140-4150

Piston Outside Diameter: $34.20 \text{ mm} \pm 0.25 \text{ mm}$ D1) Barrel Diameter Outside: $39.60 \text{ mm} \pm 0.75 \text{ mm}$ D2) Barrel Collar Diameter: $52.00 \text{ mm} \pm 0.75 \text{ mm}$ D3) Piston Collar Diameter: $42.00 \text{ mm} \pm 0.65 \text{ mm}$ L) Length: $275.00 \text{ mm} \pm 0.65 \text{ mm}$

Increment: 5.0 ml

Volume: 150.0 ml \pm 1.5% of volume

Features:

- The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- · It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at luer lock tip and barrel base, the points at which most breakage occur.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- · Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes are available in custom fit design. The custom fit syringes are uniquely numbered for matching piston and barrel.
- The metal luer lock tip meets the specification of American National Standards for Medical Materials luer taper fitting performance, HIMA MD 70.1 - 1983.
- The metal luer lock fitting is made from chrome-plated brass and fits all female luer lock fittings.
- The syringe is clearly marked with graduations of 5.0 ml and 10 ml. The graduations are permanently fused for lifetime legibility.

Glass Properties:

Expansion coefficient:	52 +/- 10 ⁻⁷ / Centigrade	S
Density:	2.36g +/- 0.03g CM ³	M
Modulus of elasticity:	64 +/- 10 ³ mm ⁻²	S
Water resistance:	First Class	Α
Acid resistance:	First Class	Н
Alkali resistance:	First Class	c

Softening point: 785 @ degrees centigrade

Melting temperature: 1260 @ degrees centigrade

Strain point: 525 @ degrees centigrade

Annealing point: 570 @ degrees centigrade

Hardness: 7

Tel: 916.429.7240

Fax: 916.429.2701

Hardness: 7
Color: Clear